



# LANKO 110

## SKIM COAT SMOOTHING RENDER

SUITABLE FOR INTERIOR AND EXTERIOR WALLS  
AND CEILINGS

### FEATURES & BENEFITS

- Easy to use
- Perfect smooth finish
- Adjustable consistency
- Good trowelability on application
- No primer required

### PACKAGING

Available in a 15kg bag

### WHERE TO USE

Davco Lanko Skim Coat Smoothing Render is a pre-blended powder that only requires mixing with clean water for repairing surface defects in concrete or render. A smooth surface is obtained by eliminating blemishes such as grooves, seams, fine cracks, blow holes and rock pockets.

### Uses

Suitable for the repair of interior and exterior walls and ceilings on surfaces such as reinforced concrete, precast concrete panels and traditional rendering.

### PRODUCT INFORMATION

#### Coverage

15kg bag of Lanko Skim Coat Smoothing Render covers approximately 1.3 kg/m<sup>2</sup>/mm

#### Application

0.3-4mm thickness

#### Set Time

Final set time 2 hours



**MADE IN  
AUSTRALIA**

## TECHNICAL

TECHNICAL DATA	LANKO 110
Appearance	Grey powder
Shelf life when stored unopened in dry and frost-free locations	6 months
Particle size	< 0.2 mm
Apparent powder density	1.13 kg/L
Wet density	1.75 kg/L
Water ratio	34-37%
pH	12
Pot life at 20°C	40 minutes

Values presented are typical and not necessarily referenced to create specifications. All measurements are taken at 20°C and 50% relative humidity. Specifications vary according to site conditions and should be taken as a guide only.

TEST DATA	TYPICAL TEST RESULT	
<b>Setting time</b>		
Initial set at 20°C		1 hr 15 minutes
Final set at 20°C		1 hr 30 minutes
<b>Test method: AS/NZS 2350.11-1997</b>		
Compressive strength	7 days	11 MPa
	28 days	12 MPa
<b>Tensile adhesion</b>		
Tensile adhesion pull up strength 3mm on concrete block	28 days	≥ 0.7 Mpa



Quality  
ISO 9001  
SAI GLOBAL

ParexGroup products manufactured in Australia are produced in accordance with quality management systems certified as complying with AS/NZS ISO 9001:2008.



## DIRECTIONS FOR USE

- A test should be undertaken in all cases to ensure suitability

## SURFACE PREPARATION

- The substrate must be clean, sound, dust-free and without any traces of oil, laitance, paint or curing compound
- Overplus and seams must be struck off
- Soak the substrate before application

## MIX PREPARATION

### Mix Ratio

SITUATION / REQUIREMENT	MIX REQUIREMENTS PER 15KG
General applications	5.1-5.5L of clean, potable water

## Mix Process

- A 15kg bag of Lanko 110 Skim Coat Smoothing Render requires 5.1-5.5 litres of clean water (i.e. 34-37% water content)
- Machine mix or hand mix until the compound is smooth and evenly distributed
- Leave the mixture to stand for several minutes then remix

## APPLICATION

- Apply mortar with a stainless steel trowel or float.
- Depending on application thickness required or desired finish, one or more coats may be applied.
- The surface of Lanko 110 Skim Coat Smoothing Render can be sanded if required.

## Clean-up & Return to Service

- Clean mixing and application equipment with water immediately after use
- Remove splatter or spills with water before material sets

## PRECAUTIONS

### Safety

- SDS is available from [www.parexdavco.com.au](http://www.parexdavco.com.au)
- It is recommended that applicators wear PVC or similar gloves and safety goggles while handling this product
- Keep out of reach of children. If eye contact occurs, rinse with cool water
- If ingested get immediate medical assistance

## General

- Do not use when temperatures are below 5°C or above 35°C
- In hot conditions, protect the finished surface from drying out by lightly misting

## Specific

- Do not apply to gypsum-based substrates
- Do not immerse the product
- For other uses not mentioned in these instructions, please contact ParexGroup



1800 653 347

[parexdavco.com.au](http://parexdavco.com.au)

[technical@parexdavco.com.au](mailto:technical@parexdavco.com.au)

[facebook.com/parexdavco](https://facebook.com/parexdavco)

PAREX reserves the right to inspect any alleged failure at our cost. No responsibility will be accepted unless a representative of PAREX is afforded the opportunity to inspect any alleged failure.